CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-01-31-86** **Date: 02/08/2019**

Customer : Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.

Address : T-Dasarahalli Sub Division, BBMP, Bangalore.

Project Name : Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15

Agency : Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.

Customer's Reference : EE/SWD/DHZ/WO/06/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 08-07-19

Customer ID : Cement Concrete pavement

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M30 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 02/08/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm²)	Average Compressive Strength (N/mm²)
1	Cement Concrete pavement	M30	05/07/2019	02/08/2019	150.82 X 149.11 X 149.64	22489	8.877	743.3	33.1	32.9
2	Cement Concrete pavement	M30	05/07/2019	02/08/2019	149.56 X 151.91 X 149.70	22719	8.080	731.9	32.2	
3	Cement Concrete pavement	M30	05/07/2019	02/08/2019	150.27 X 149.51 X 150.03	22467	8.433	749.8	33.4	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned with CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 12/07/2019

Lab ID	:	CP-2020-01-31-86
Customer	:	Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T-Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15
Agency	:	Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.
Customer's Reference	:	EE/SWD/DHZ/WO/06/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	08-07-19
Customer ID	:	Cement Concrete pavement
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M30 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	12/07/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete pavement	M30	05/07/2019	12/07/2019	149.49 X 149.62 X 149.92	22368	8.220	561.5	25.1	25.3
2	Cement Concrete pavement	M30	05/07/2019	12/07/2019	149.00 X 149.97 X 150.90	22346	8.651	587.8	26.3	
3	Cement Concrete pavement	M30	05/07/2019	12/07/2019	150.91 X 151.23 X 149.18	22822	8.121	561.5	24.6	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned with CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No. CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 02/08/2019

Lab ID	:	CP-2020-01-31-86
Customer	:	Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T-Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15
Agency	:	Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.
Customer's Reference	:	EE/SWD/DHZ/WO/06/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	08-07-19
Customer ID	:	Cement Concrete pavement
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M30 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	02/08/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm²)	Average Compressive Strength (N/mm²)
1	Cement Concrete pavement	M30	05/07/2019	02/08/2019	151.14 X 151.54 X 149.61	22904	8.877	769.2	33.6	33.0
2	Cement Concrete pavement	M30	05/07/2019	02/08/2019	149.29 X 150.55 X 151.26	22476	8.080	724.3	32.2	
3	Cement Concrete pavement	M30	05/07/2019	02/08/2019	149.15 X 151.12 X 150.41	22539	8.433	747.1	33.1	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned with CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 08/07/2019

Lab ID	:	CP-2020-01-31-86
Customer	:	Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T-Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15
Agency	:	Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.
Customer's Reference	:	EE/SWD/DHZ/WO/06/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	03-07-19
Customer ID	:	Drain Bottom Slab Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	08/07/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm²)	Average Compressive Strength (N/mm²)
1	Drain Bottom Slab Concrete	M20	01/07/2019	08/07/2019	149.74 X 149.51 X 151.25	22388	8.111	423.9	18.9	18.6
2	Drain Bottom Slab Concrete	M20	01/07/2019	08/07/2019	151.10 X 149.24 X 150.42	22549	8.445	408.7	18.1	
3	Drain Bottom Slab Concrete	M20	01/07/2019	08/07/2019	151.42 X 149.26 X 150.21	22601	8.966	422.2	18.7	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

Scanned with CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 29/07/2019

Lab ID	:	**CP-2020-01-31-86**
Customer	:	Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T-Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15
Agency	:	Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.
Customer's Reference	:	EE/SWD/DHZ/WO/06/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	03-07-19
Customer ID	:	Drain Bottom Slab Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	29/07/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Slab Concrete	M20	01/07/2019	29/07/2019	151.62 X 150.38 X 149.54	22801	8.774	545.1	23.9	23.3
2	Drain Bottom Slab Concrete	M20	01/07/2019	29/07/2019	151.08 X 150.70 X 149.85	22767	8.635	510.2	22.4	
3	Drain Bottom Slab Concrete	M20	01/07/2019	29/07/2019	150.46 X 151.98 X 151.02	22867	8.782	537.7	23.5	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned with CamScanner

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 10/07/2019

Lab ID	:	CP-2020-01-31-86
Customer	:	Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T-Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15
Agency	:	Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.
Customer's Reference	:	EE/SWD/DHZ/WO/06/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	05-07-19
Customer ID	:	Drain Side Wall Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	10/07/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M20	03/07/2019	10/07/2019	150.83 X 151.01 X 151.27	22777	8.111	418.8	18.4	18.4
2	Drain Side Wall Concrete	M20	03/07/2019	10/07/2019	150.02 X 151.73 X 150.70	22762	8.445	429.5	18.9	
3	Drain Side Wall Concrete	M20	03/07/2019	10/07/2019	150.06 X 149.38 X 149.22	22415	8.966	404.7	18.1	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

Scanned with CamScanner

CIVIL PRO

AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005

4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 31/07/2019

Lab ID	:	CP-2020-01-31-86
Customer	:	Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T-Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15
Agency	:	Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.
Customer's Reference	:	EE/SWD/DHZ/WO/06/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	05-07-19
Customer ID	:	Drain Side Wall Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	31/07/2019

SL No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M20	03/07/2019	31/07/2019	151.62 X 150.34 X 149.25	22796	8.774	526.7	23.1	23.0
2	Drain Side Wall Concrete	M20	03/07/2019	31/07/2019	150.69 X 149.87 X 150.51	22585	8.635	513.4	22.7	
3	Drain Side Wall Concrete	M20	03/07/2019	31/07/2019	151.92 X 150.60 X 151.11	22879	8.782	528.9	23.1	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned with CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-554

TEST RESULTS FOR CHAIN LINK FENCING

Date: 07-05-19

Lab ID	:	CP-2019-09-11-27
Customer	:	Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T-Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15
Agency	:	Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.
Customer's Reference	:	EE/SWD/DHZ/WO/06/2017-18
Sourse of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	06-05-19
Type of Sample	:	Chain Link Fencing
Reference to BIS codes	:	IS 2062:2011
Date of testing	:	06-05-19

TESTS RESULT FOR WIRE MESH		
SL.NO	**Description**	**Result**
1	**Average Thickness in mm**	4.04
2	**Dia of linewire in mm**	3.14
3	**Mesh size in mm**	50.01
4	**Nominaldia of meshwire in mm**	2.52
5	**Bend Test**	Satisfactory

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative.
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com
HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |

Scanned with CamScanner

TEST RESULTES FOR MS BLOCK PIPE

Lab ID	:	**CP-2019-08-14-45** **Date: 04-05-19**
Customer	:	Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T-Dasarahalli Sub Division, BBMP, Bangalore.
Agency	:	Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15
Project Name	:	Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.
Customer's Reference	:	EE/SWD/DHZ/WO/06/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	03-05-19
Type of Sample	:	M.S Block Pipe
Reference to BIS codes	:	IS:1608-2005(RA 2011), IS 1599-2012.
Date of testing	:	03-05-19

TESTS RESULTS FOR MS BLOCK PIPE 38MM DIA, 14 GAUGE

Sl. No	Description	Result	Required as per as IS Code 2062: 2011	Remarks
1	Yeild Stress (N/mm2)	299	250N/mm^2	Satisfactory
2	Tensile Strength (N/mm2)	509	410N/mm^2	Satisfactory
3	Elongation Percentage (%)	24	Min 23%	Satisfactory

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned with CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

TEST RESULTES FOR MS RECTANGULAR POLE

Lab ID : **CP-2019-08-14-45** **Date: 08-05-19**

Customer : Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.

Address : T-Dasarahalli Sub Division, BBMP, Bangalore.

Project Name : Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15

Agency : Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.

Customer's Reference : EE/SWD/DHZ/WO/06/2017-18

Sourse of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 07-05-19

Type of Sample : M.S Rectangular Pole(65X65X6)mm

Reference to BIS codes : IS:1608-2005(RA 2011), IS 1599-2012.

Date of testing : 07-05-19

TESTS RESULTS FOR M.S RECTANGULAR POLES MADE OUT OF 2 EQUAL ANGLES OF 65 X 65 X 6 MM WELDED TOGETHER

SL.NO	Description	Result	Required as per IS Code 2062:2011	Remarks
1	Weight/Meter (Kg /m)	5.81	5.8 Kg/m	Satisfactory
2	Yeild stress (N/mm2)	278	250N/mm^2	Satisfactory
3	Tensile Strength (N/mm2)	485	410N/mm^2	Satisfactory
4	Elongation Percentage (%)	23.5	Min23%	Satisfactory
5	Bend Test	Satisfactory	Should not Crack or fracture	Satisfactory

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative.
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com
HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned with CamScanner